

→ **system**

Product Data-Sheet

No. 9413 - RV - 04

Edition: Jan 2011

1. Application Sector

DAMTEC® system is the premium insulating padding for concrete or wooden subfloors. It provides outstanding impact sound deadening properties under screed or rigid floor elements. **DAMTEC® system's** special design and granular-textured surface ensure superior acoustic insulation especially in the low frequency range, the most difficult part of impact sound insulation. **DAMTEC® system** is ideal for use on wooden subfloors in combination with flooring of various types, generating high market demand particularly in the refurbishment sector.

2. Material

Two-layer compound with rubber granules and rubber mat with PU elastomer bonding agent

3. Appearance

colour:	black
upper side:	open granules
lower side:	smooth with fine granular texture

4. Dimensions/Tolerances

width:	1,000mm ± 1.5 %
length:	10,000mm ± 1.5 %
thickness:	approx. 6mm
area weight:	approx. 3.1kg/m ²

→ system

Product Data-Sheet

No. 9413 - RV - 04

Edition: Jan 2011

5. Physical Characteristics

tensile strength:	approx. 0.6N/mm ²	(ISO 1798)
elongation at break:	approx. 40%	(ISO 1798)
impact sound improvement:	$\Delta L_W = 23\text{dB}$ 1-layer under screed $\Delta L_W = 26\text{dB}$ 2-layer under screed $\Delta L_W = 21\text{dB}$, $\Delta L_{in} = 10\text{dB}$ 2-layer with 22mm solid oak	(ISO 140-8)
impact sound level:	$L_{n,w} = 42\text{dB}$ on wooden floor	(ISO 140-7)
max. steady load:	0.05 N/mm ²	(EN 826)
dynamic stiffness:	< 15 MN/m ³	(EN 29052)
heat transmission coefficient:	0.07m ² K/W (one layer)	(DIN 52612)
heat transfer coefficient:	14 W/m ² K (one layer)	
heat conductivity:	0.09 W/mK	

DAMTEC® system meets the demands of AgBB scheme and is suitable for use in interior of buildings. (test report no. 155033, ihd Dresden)

6. Installation

Construction and installation is to be carried out in accordance with the **DAMTEC® system** technical information.

DISCLAIMER:

The information provided is intended only as a summary and general overview on matters of interest. The information is not intended to be comprehensive nor does it constitute expert advice. KRAIBURG RELASTEC shall not be liable for incidental and/or consequential damages directly or indirectly sustained, nor any loss caused by not complying with relevant industry/product standards and improper use of any Damtec® products. Due to varying construction methods, any other circumstances not stated above should be brought to the attention of KRAIBURG RELASTEC for review. For suitability to the prevailing site conditions, it is advised that certified testing should be conducted. It is recommended to seek further advice on your application with our technical staff prior to use.

The data sheet is not subject to any change service! All information is without guarantee.
Latest version of this document available on www.kraiburg-relastec.com/damtec