

→ **estra**

Product Data-Sheet

No. 9406 - R - 05

Edition: Jan 2011

1. Application Sector

DAMTEC® estra is the ideal rubber underlay in floating screed /concrete slab systems or underneath rigid floor elements on wooden sub floors.

DAMTEC® estra is particularly quick and easy to install and is providing extremely high resistance to compressive loads and outstanding elasticity. It is equally well suited for applications in residential, office and commercial buildings.

2. Material

Granules of recycled rubber with PU elastomer bonding agent

3. Appearance

colour:	multicolour
surface:	granular texturing

4. Dimensions/Tolerances

width:	1250 mm	± 1.5 %
length:	on request	± 1.5 %
available thickness:	4, 6, 8 mm	± 0.3 mm
density:	approx. 820 kg/m ³	

→ **estra**

Product Data-Sheet

No. 9406 - R - 05

Edition: Jan 2011

5. Physical Characteristics

tensile strength:	approx. 0.4 N/mm ²	(ISO 1798)
elongation at break:	approx. 50 %	(ISO 1798)
service temperature range:	- 30°C bis 80°C	
flammability rating:	B 2	(DIN 4102-1)
heat transmission coefficient:	0.05 m ² K/W for 6mm slab	(DIN 52612)
dynamic rigidity:	4mm < 90 MN/m ³ 6mm < 70 MN/m ³ 8mm < 60 MN/m ³	(EN 29052)
maximum load:	0.2 N/mm ²	(in Acc. to EN 826)
impact sound improvement:	$\Delta L_w = 19\text{dB}$ with 4mm under screed $\Delta L_w = 20\text{dB}$ with 6mm under screed $\Delta L_w = 21\text{dB}$ with 8mm under screed	(ISO 140-8)

6. Installation

Installation is to be carried out in accordance with the **DAMTEC®** **estra** installation instructions.

DISCLAIMER:

The information provided is intended only as a summary and general overview on matters of interest. The information is not intended to be comprehensive nor does it constitute expert advice. KRAIBURG RELASTEC shall not be liable for incidental and/or consequential damages directly or indirectly sustained, nor any loss caused by not complying with relevant industry/product standards and improper use of any Damtec® products. Due to varying construction methods, any other circumstances not stated above should be brought to the attention of KRAIBURG RELASTEC for review. For suitability to the prevailing site conditions, it is advised that certified testing should be conducted. It is recommended to seek further advice on your application with our technical staff prior to use.

The data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on www.kraiburg-relastec.com/damtec

Page 2/2

