

## → ceramic / ceramic plus

### Product Data-Sheet

No. 9407 - RV - 02

Edition: Jul 2010

### 1. Application Sector

**DAMTEC® ceramic plus** is an impact sound and a decoupling underlay with two-layered structure for stoneware and ceramic tiles. Pure rubber granulates with additional fleece lamination makes an optimal transverse extension behaviour possible.

**DAMTEC® ceramic** is a decoupling course from pure rubber granulates. It decouples reliably the floor structure of tile floors and stoneware and prevents thereby cracking.

**DAMTEC® ceramic** and **DAMTEC® ceramic plus** are highly loadable and well suitable for wet rooms under stoneware and ceramic tiles.

### 2. Material

#### **DAMTEC® ceramic:**

Granules of recycled rubber with PU elastomer bonding agent

#### **DAMTEC® ceramic plus:**

top surface: Granules of recycled rubber with PU elastomer bonding agent

lower surface: 100% PET recycling fibres, mechanically ennobles

### 3. Appearance

colour: black (**DAMTEC® ceramic**), multicoloured (fleece)

surface: granular texture (**DAMTEC® ceramic**)  
fibrous structure (fleece)

### 4. Dimensions/Tolerances

	<b>DAMTEC® ceramic:</b>	<b>DAMTEC® ceramic plus:</b>
width:	1,250mm ± 1.5 %	1,000mm ± 1.5%
length:	± 1.5%	10,000mm ± 1.5%
available thickness:	3, 4, 5, 6mm ± 0.3mm	3mm ± 0.3mm
thickness fleece:		approx. 2.5mm
density:	790 - 890kg/m <sup>3</sup>	
area weight:		approx. 1,260g/m <sup>2</sup>

Seite 1/2



Made in  
Germany



→ **ceramic / ceramic plus**

## Product Data-Sheet

No. 9407 - RV - 02

Edition: Jul 2010

### 5. Physical Characteristics

tensile strength (EN ISO 1798):	<b>ceramic:</b> approx. 0.6 N/mm <sup>2</sup>	<b>ceramic plus:</b> approx. 1.3N/mm <sup>2</sup>
elongation at break (EN ISO 1798):	approx. 40%	approx. 50%
service temperature range:	- 30°C to 80°C	- 30°C to 80°C
heat transmission coef. (DIN 52612):	3mm = 0.03 m <sup>2</sup> K/W	0.05 m <sup>2</sup> K/W
flammability rating (DIN 4102-1):	E <sub>fl</sub>	E <sub>fl</sub>
impact sound improve (EN ISO 140-8):		ΔL <sub>w</sub> = 16dB

### 6. Installation

Installation is to be carried out in accordance with the **DAMTEC® ceramic** installation instructions.

Castor chair behaviour and residual indentation after static loading of the flooring can change in accordance with the insulating underlay used.

Only use underlay approved by the floor manufacturer.

Prior to any installation work, carefully read and observe the usage instructions and processing guidelines of the adhesive cement and floor finish manufacturers.

In case of doubt, please contact the manufacturer's applications engineering department for advice.

#### DISCLAIMER:

The information provided is intended only as a summary and general overview on matters of interest. The information is not intended to be comprehensive nor does it constitute expert advice. KRAIBURG RELASTEC shall not be liable for incidental and/or consequential damages directly or indirectly sustained, nor any loss caused by not complying with relevant industry/product standards and improper use of any Damtec® products. Due to varying construction methods, any other circumstances not stated above should be brought to the attention of KRAIBURG RELASTEC for review. For suitability to the prevailing site conditions, it is advised that certified testing should be conducted. It is recommended to seek further advice on your application with our technical staff prior to use.

The data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on [www.kraiburg-relastec.com/damtec](http://www.kraiburg-relastec.com/damtec)

Seite 2/2



Made in  
Germany

